

SELECTION & SPECIFICATION DATA

Type Epoxy Modified Acrylic

Description A waterborne epoxy modified elastomeric acrylic that

provides a tough, monolithic, flexible membrane for use

as a white roof restoration coating.

Features • Water-based with low VOC's

Rapid setting

• Elastomeric properties

Sag proof

· Easily repairable

Uses • Roofing

· Moisture/vapor barrier

Color White

Finish Matte

Dry Film Thickness 30 - 60 mils per coat

(DFT)
Solids

Content

48% by weight 45% by volume

Limitations

Protect from freezing Not for immersion service

SUBSTRATES & SURFACE PREPARATION

All Substrate must be clean, dry and free of contaminants.

Previously Painted Surfaces Consult with ErgonArmor Technical Service.

MIXING & THINNING

Mixing Gentle agitation recommended

Thinning Do not thin

Ratio Two component. Set ratio through proprietary spray

equipment. Consult with ErgonArmor Technical Service.

Cleanup Tools and hands should be cleaned with water.

Spray equipment should be flushed with water.

APPLICATION GUIDANCE

Spray Application Ertech 7365 is designed for spray application using proprietary equipment that co-sprays Ertech 7365 and an accelerator that rapidly sets the sprayed film. For information on spray equipment consult with ErgonArmor Technical Service.

Film Thickness A film thickness of up to 125 mils wet can be achieved on vertical surfaces without sagging. For applying films thicker than 125 wet mils, consult with ErgonArmor Technical

Service.

Temperature Use in temperatures of 50°F (10°C) or higher for best

performance.

Dry-To-Touch 15 minutes at 77°F (25°C). Cure times are decreased with air

movement over the coating.

Full Cure 36 - 72 hours at 77°F (25°C). Cure times are decreased with

air movement over the coating.



PACKAGING, ESTIMATING & HANDLING

ITEM# PACKAGING

K-7365-275-001 IBC Tote - 275 gallons

Theoretical Coverage

722 square feet per gallon at 1 mil DFT

Storage & Shelf Life

Estimated shelf life is 6 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 50°F (10°C) or above 110°F (43°C). Protect from freezing. Do not

store product outside. Store indoors.

SAFETY

SafetyMixes and applications of this product present a number of hazards. Read and follow the hazard

information, precautions and first aid directions on the individual product labels and safety data

sheets before using.

Ventilation Use in well ventilated areas.

TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.9 lbs/gal
Solids by weight ASTM D5201-05a	48%
Solids by volume ASTM D5201-05a	45%
Specific gravity	1.07
Dry-to-touch, 77°F (25°C) ASTM D5895-96	15 minutes
Full cure, 77°F (25°C)	36 - 72 hours
Viscosity, 77°F (25°C) ASTM D2983-19	50 - 250 cps
Resistance to oils, greases and solvents	Poor
VOC	0.2 lbs/gal maximum
Permeance 60 mils nominal ASTM E96 A method	0.06 perms
Permeance 60 mils nominal ASTM E96 B method	0.08 perms
Tensile strength ASTM D2370-16	155 psi
Elongation ASTM-16	643.5%

Rev. 09/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.