

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Wet/Dry Roof Flashing Cement
<b>Description</b>	Blackhawk 5405 Wet/Dry Roofing Cement is an asbestos-free, fiber reinforced asphalt roofing cement that bonds to wet substrates.
<b>Uses</b>	Blackhawk 5405 Wet/Dry Roofing Cement has a variety of uses including: <ul style="list-style-type: none"> <li>• Night seals</li> <li>• Vertical flashings</li> <li>• Three coursing</li> <li>• Setting roof drains</li> <li>• Seals end laps, side laps and shingle tabs</li> </ul>
<b>Color</b>	Black
<b>Primer</b>	Self-priming
<b>Topcoats</b>	Can be topcoated with urethane, acrylic or silicone. It can also receive granule embedment while still wet.
<b>Finish</b>	Black. Chalked grey over time
<b>Dry Film Thickness (DFT)</b>	1/8-inch is typical
<b>Solids Content</b>	85% by volume
<b>VOC Value(s)</b>	<250 g/l (2.09 lbs/gal)

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
---------------	--

## MIXING & THINNING

<b>Mixing</b>	No mixing required. Ready to use as is.
<b>Thinning</b>	Do not thin

## APPLICATION GUIDANCE

<b>Trowel</b>	1/8-inch serrated trowel or round/bullnose roofing trowel
---------------	---

<b>Cleanup</b>	Mineral spirits or equivalent solvent.
----------------	--

## PACKAGING, ESTIMATING & HANDLING

ITEM #	PACKAGING
K-5405-005-001	Pail - 4.7 gallons

<b>Theoretical Coverage</b>	14 square feet per gallon at 1/8-inch thickness
-----------------------------	---

<b>Storage &amp; Shelf Life</b>	Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions.
---------------------------------	---

Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the product prior to use to make sure it is smooth and homogeneous.

## TYPICAL PHYSICAL PROPERTIES

SPECIFICATIONS	CATEGORY	RESULTS
ASTM 3409	Wet Adhesion	Pass
ASTM 4586	Type 1	Pass
ASTM 6511	Uniformity	Pass
ASTM 6511	Workability	Pass
ASTM 6511 Blistering	Behavior at 140°F (60°C)	None
ASTM 6511 Cracking	Pliability at 32°F (0°C)	Pass
Sag/Slide	Behavior at 140°F (60°C)	Pass

Rev 12/21

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).